

| ~ | rass | 7 | 1 | / | - 11 | ~ - I | | |
|---|------|-----|-----|------|------|----------|-----|--|
| | racc | 701 | וםר | /arı | n/I | ^ | ınr | |
| | | | | | | | | |

Grass Zone Denier

Thatch Zone Yarn/Color

Thatch Zone Denier

Grass Zone Yarn Shape

Finished Pile Height

Finished Pile Weight

Backing

Tuft Gauge

Total Weight

Tuft Bind

Permeability

Features

Test Data

PE / Field Green / Apple

10,800 / 6

PE / Field Green / Beige

5,000/8

'S' Shape

1 1/2"

60 oz.

15 / 18 PP 2-Part / 20oz. EnviroLoc™

3/8"

86 oz.

> 8 lbs.

> 300 inches per / SY

EnviroLoc™, HeatBlock™, Deluster, **UV Stabilizers**

ASTM Certified F1292, F1551, F1951

SYNPro 60

Stunning realism at a budget-friendly value make this artificial grass a perfect fit for those seeking premium quality at a economical price.



Unmatched Lifetime Warranty



EnviroLoc™ Plant-Based Backing



Deluster and UV Protection



Softness



RECOMMENDED USES

























| Primary Yarn Polymer | Polyethylene | | |
|----------------------------|---------------------|--|--|
| Yarn Cross Section | 'S' Shape | | |
| Standard Color | Field Green / Apple | | |
| Fabric Construction | Tufted | | |
| Second Yarn Polymer Thatch | Polyethylene | | |
| Secondary Yarn Color | Field Green / Beige | | |

| Primary Backing | 15/18 PP 2-Part | | | |
|---------------------------------|-------------------|--|--|--|
| Coating Type | 20 oz. EnviroLoc™ | | | |
| PE Yarn Denier / Ends | 10,800 / 6 | | | |
| Texturized Thatch Denier / Ends | 5,000 / 8 | | | |
| Warranty Period | Limited Lifetime | | | |

| Finish Fabric English System | | System | ASTM Test | |
|------------------------------|--------|--------|-----------|--|
| Nominal Specification | Value | Units | Method | |
| Pile Height (Nominal) | 1 1/2 | inches | D-5823 | |
| Face Weight | 60 | oz/yd² | D-5848 | |
| Total Fabric Weight | 86 | oz/yd² | D-5848 | |
| Primary Backing Weight | 6 | oz/yd² | D-5848 | |
| Secondary Coating Weight | 20 | oz/yd² | D-5848 | |
| Tuft Bind | > 8 | lbs. | D-1335 | |
| Grab Tear Strength (Average) | > 200 | lbs. | D-5034 | |
| Total Yarn Linear Density | 15,800 | Denier | D-1577 | |
| Elongation to Break | > 30 | % | D-2256 | |
| Yarn Breaking Strength | > 20 | lbs. | D-5793 | |
| Machine Guage | 3/8 | inches | D-5793 | |
| Flammability | Passed | - | D-2859 | |
| Water Permeability | 344.31 | in/hr | D-1551 | |
| Fabric Width | 15 | ft | - | |





