



| Grass | 7000 | Vara | $ C_{\alpha} _{\alpha}$ | |
|-------|------|------|-------------------------|---|
| เมสรร | /one | Yam | (LOIO) | 1 |

Grass Zone Denier

Thatch Zone Yarn/Color

Thatch Zone Denier

Grass Zone Yarn Shape

Finished Pile Height

Finished Pile Weight

Backing

Tuft Gauge

Total Weight

Tuft Bind

Permeability

Features

Test Data

PE / Field Green / Apple

10,000 / 6

PE / Turf Green

5,040 / 12

Omega

1 5/8"

80 oz.

15 / 18 PP 2-Part / 20oz. EnviroLoc™

3/8"

106 oz.

> 8 lbs.

> 400 inches per / SY

Sanitized®, EnviroLoc™, StatBlock™ Anti-Static, DualChill™ IR Reflective, Deluster, UV Stabilizers

ASTM F1292, F1551, F1951

SYNTipede 321

Just like its natural counterpart, SYNTipede is known for being tough. The tallest in the collection including Super Yarn™ technology creating a durable surface perfect for active children and pets. ASTM E108 Class A Fire-Rated provides peace of mind for all types of projects.



Unmatched Lifetime Warranty



EnviroLoc™ Plant-Based Backing



Deluster and UV Protection



Class A Fire Rating







SUPER YARN[™] TECHNOLOGY

Sanitized® Antimicrobial **DualChill**™ IR Reflective

StatBlock™ Anti-Static



RECOMMENDED USES



















| Primary Yarn Polymer | Polyethylene | |
|----------------------------|---------------------|--|
| Yarn Cross Section | Omega | |
| Standard Color | Field Green / Apple | |
| Fabric Construction | Tufted | |
| Second Yarn Polymer Thatch | Polyethylene | |
| Secondary Yarn Color | Turf Green | |

| Primary Backing | 15/18 PP 2-Part | | |
|---------------------------------|-------------------|--|--|
| Coating Type | 20 oz. EnviroLoc™ | | |
| PE Yarn Denier / Ends | 10,000 / 6 | | |
| Texturized Thatch Denier / Ends | 5,040 / 12 | | |
| Warranty Period | Limited Lifetime | | |

| Finish Fabric | English | System | ASTM Test |
|------------------------------|---------|--------|-----------|
| Nominal Specification | Value | Units | Method |
| Pile Height (Nominal) | 1 5/8 | inches | D-5823 |
| Face Weight | 80 | oz/yd² | D-5848 |
| Total Fabric Weight | 106 | oz/yd² | D-5848 |
| Primary Backing Weight | 6 | oz/yd² | D-5848 |
| Secondary Coating Weight | 20 | oz/yd² | D-5848 |
| Tuft Bind | > 8 | lbs. | D-1335 |
| Grab Tear Strength (Average) | > 200 | lbs. | D-5034 |
| Total Yarn Linear Density | 15,040 | Denier | D-1577 |
| Elongation to Break | > 30 | % | D-2256 |
| Yarn Breaking Strength | > 20 | lbs. | D-5793 |
| Machine Guage | 3/8 | inches | D-5793 |
| Flammability | Passed | - | D-2859 |
| Water Permeability | 425 | in/hr | D-1551 |
| Fabric Width | 15 | ft | - |





